

Purolite® MB400

**Polystyrenic Gel Mixed Bed
Resin Hydrogen form Hydroxide
Form**

PRINCIPAL APPLICATIONS

- Demineralization - Mixed Bed
- Cartridges

ADVANTAGES

- General purpose

SYSTEMS

- Coflow regenerated systems
- Counterflow regenerated systems
- Mixed Bed

REGULATORY APPROVALS

- IFANCA Halal Certified

TYPICAL PACKAGING

- 1 CF Sack
- 25 L Sack
- 5 CF Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical beads	
Moisture Content (max.)	65 %	
Particle Size Range	300 - 1200 µm	
< 300 µm (max.)	1 %	
Uniformity Coefficient (max.)	1.7	
Shipping Weight (approx.)	705 - 740 g/L (44.1 - 46.2 lb/ft³)	
Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F)	
Temperature Limit, Regenerable Bed	60 °C (140.0 °F)	
Component Name	Gel Strong Acid Cation	Gel Type I Strong Base Anion
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H ⁺	OH ⁻
Cation / Anion Volumetric Ratio	40 %	60 %



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

Europe
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com